

EXECUTIVE 309LMo

STAINLESS STEEL

SOLID WIRE TECHNICAL DATA SHEET

DESCRIPTION

Executive ER309LMo wire is designed to provide clean and consistent welds with excellent feedability and minimal clean-up. By maintaining tight control from the country of melt to the design of the spool Executive wire provides welders with the highest quality stainless bare wire.

Executive ER309LMo has additional Molybdenum which gives it better strength, crack and corrosion resistance at high temperature.

Executive ER309LMo has a maximum carbon level of 0.03% which enhances the resistance to intergranular corrosion.

APPLICATIONS & FEATURES

The primary application for Executive ER309LMol is surfacing of base metals to improve their corrosion resistance. In multilayer overlays, the low carbon Executive 309LMo is usually needed for the first layer in order to achieve low carbon contents in successive layers with filler metals such as Executive 316L or Executive 317L. Other applications include the welding of molybdenum-containing stainless steel linings to carbon steel shells, the joining of carbon steel base metals which had been clad with a molybdenum-containing stainless steel, and the joining of dissimilar base metals such as carbon steel to Type 304 stainless steel. The ferrite level of the wire should be sufficiently high in order to stop formation of fully austenitic micro-structure with dilution from base material.

TYPICAL WIRE CHEMISTRY & MECHANICAL PROPERTIES

С	Cr	Ni	Мо	Mn	Si	Р	S	Cu	N
0.010	21.27	14.81	2.58	1.48	0.31	0.022	0.0027	0.096	0.052

Tensile Strength: 86,300 PSI min Elongation: 38.1% Ferrite Range: 9 FN (WRC-92)

Yield Strength: 60,500 PSI min

TYPICAL	WELDING PARAMETER	RS

Process	Diameter	Voltage	Amperage	Gas Flow	Shielding Gas / Flux	
GMAW - Short	.035"	21-22	160-200		000/ Ar / 20/ O	
	.045"	22-23	180-210	30 to 50 CFH	98% Ar / 2% O ₂	
- Spray	.035"	23-25	190-260	30 to 30 CFH	90% Ar / 10% O ₂	
	.045"	25-28	250-330		90% At / 10% O ₂	
GTAW	.093"	Direct Currer	Direct Current; Electrode -		100% Ar	
SAW	.093"	29-32	300-350		Record IN Flux	
	.125"	29-32	400-550		RECOLU IIN FIUX	

STANDARD PACKAGING

GMAW (MIG)	33-lb wire baskets 11-lb plastic spools 2-lb plastic spools	1,980-lb pallet 11-lb box 8-lb box
GTAW (TIG)	10-lb plastic tube	40-lb box
SAW	60-lb wire coil	1.200-lb pallet

CLASSIFICATION

AWS/SFA 5.9, Class ER309MLo

