

DESCRIPTION

Executive 309/309L provides superior weldability, low spatter and smooth beads with easy slag removal. Used to join similar 309L alloy or join 300 series stainless steel to carbon or low alloy steels. Recommended for use as the first layer in a single or multilayer surfacing of non-alloy and low-alloy steels to give 304L deposit.

This wire is designed to be used for welding in all positions. Low carbon in this filler metal reduces the possibility of intergranular carbide precipitation. This increases the resistance to intergranular corrosion without the use of stabilizers such as niobium or titanium. Strength of this low-carbon alloy, however, is less than that of the niobium-stabilized alloys or Type 309 at elevated temperatures.

APPLICATIONS & FEATURES

Used for welding similar alloys in wrought or cast form; occasionally, to weld type 304 base metals when severe corrosion conditions exist; and welding dissimilar steels.

TYPICAL WIRE CHEMISTRY & MECHANICAL PROPERTIES

C	Cr	Ni	Mo	Mn	Si	P	S	Cu	
0.02	22.72	12.36	0.09	1.35	0.95	0.03	0.01	0.07	
Tensile Strength:		82,700 PSI min						Elongation:	38%
Yield Strength:		70,000 PSI min							

TYPICAL WELDING PARAMETERS

Diameter	Voltage	Amperage	WFS (in/min)	Shielding Gas*
.045"	24	130	225	100% CO ₂ or Ar + 20-25% CO ₂
.045"	27	175	320	
.045"	30	240	530	
.062"	27	195	152	100% CO ₂ or Ar + 20-25% CO ₂
.062"	31	260	260	
.062"	34	320	360	

*Shielding gas flow rate 35 to 50 CFH. For 100% CO₂ use two volts higher than shown

STANDARD PACKAGING

FCAW 33-lb plastic spools 1,980-lb pallet

CLASSIFICATION

AWS/SFA 5.22, Class **E309/309LT1-1/4**
Certified by CWB to CSA W48, Class E309/309LT1-1/4

