

DESCRIPTION

Executive 80S-B2 is designed for welding of 1-1/4Cr – ½ Mo steels using MIG or TIG welding processes where high temperature service and creep resistance is important. The alloy content of the wire produces weld metal that matches the base material and maintains mechanical properties after post-weld heat treatment. The Executive 80S-B2 also offers tightly controlled low melting residual elements to meet X factor of less than 15 in order to resist temper embrittlement.

Executive 80S-B2 filler metal is produced using high quality raw materials and tightly controlled chemistry to provide top quality, exceptionally clean wires that deliver smooth feedability and the results fabricators demand.

APPLICATIONS & FEATURES

Executive 80S-B2 is used to weld 1/2Cr-1/2Mo, 1Cr-1/2Mo, and 1-1/4Cr- 1/2Mo steels for elevated service temperatures and creep resistance such as pressure vessels and pressure piping.

Typical material grades include ASTM A387-Gr 11/12, A335-Gr 11/12 and F182-Gr 11/12.

TYPICAL WIRE CHEMISTRY & MECHANICAL PROPERTIES

C	Mn	Si	Cr	Mo	P	S	Cr	Sb	Sn	As	TOE	Cu	Ni
0.10	0.55	0.60	1.24	0.50	0.009	0.007	1.24	<0.0	0.0088	0.003	<.50	0.02	<.1

Tensile Strength:	85,000 PSI min	Yield Strength:	71,500 PSI min	Elongation:	21%
Charpy V-Notch:	60 ft/lb at 32°F / 0°C	X Factor			< 15

*PWHT 1 hour @ 1150°F/ 620°C

TYPICAL WELDING PARAMETERS

Process	Diameter	Voltage	Amperage	Speed (in/min)	Shielding Gas / Flux	
GMAW - Short	.035"	14-20	90-160	100	100% CO ₂	
	.045"	16-20	120-200	150	75% Ar / 25% CO ₂	
	- Spray	.035"	25-28	180-230	125	98% Ar / 2% O ₂
		.045"	25-30	250-350	150	75% Ar / 25% CO ₂
GTAW	.093" .125"	Direct Current; Electrode -			100% Ar	

STANDARD PACKAGING

GMAW (MIG)	33-lb plastic spools	1,980-lb pallet
GTAW (TIG)	10-lb plastic tube	40-lb box

CLASSIFICATION

AWS/SFA 5.28, Class **ER80S-B2**

