

DESCRIPTION

Executive 90S-B9 is designed to weld P91 and P92 type steels using MIG or TIG welding processes where high temperature service and creep resistance is important. The alloy content of the wire produces weld metal that matches the base material and maintains mechanical properties after post-weld heat treat. The Executive 90S-B9 offers tightly controlled low melting residual elements to meet X factor of less than 15 in order to resist temper embrittlement.

Executive 90S-B9 filler metal is produced using high quality raw materials and tightly controlled chemistry to provide top quality, exceptionally clean wires that deliver smooth feedability and the results fabricators demand.

APPLICATIONS & FEATURES

Executive 90S-B9 is used to weld P91 and P92 type materials which are used extensively for headers, main steam piping and turbine casings in fossil fuel powered power generation.

Typical material grades include ASTM A387-Gr 91, A335-P91 and A182-F91.

TYPICAL WIRE CHEMISTRY & MECHANICAL PROPERTIES

C	Mn	Si	Cr	Mo	P	S	Cu	Ni	V	Al	Nb	N	Sn	Sb	As
0.09	0.42	0.23	8.92	0.93	0.006	0.001	0.07	0.51	0.21	0.006	0.08	0.0593	0.0035	0.0	0.0015

Tensile Strength: 96,000 PSI min

Yield Strength: 81,500 PSI min

Elongation: 25%

Charpy V-Notch:

X-Factor: < 15

*PWHT 1 hour @ 1400°F / 760°C

TYPICAL WELDING PARAMETERS

Process	Diameter	Voltage	Amperage	Speed (in/min)	Shielding Gas / Flux
GMAW - Short	.035"	14-20	90-160	100	100% CO ₂
	.045"	16-20	120-200	150	75% Ar / 25% CO ₂
	- Spray	25-28	180-230	125	98% Ar / 2% O ₂
	.045"	25-30	250-350	150	75% Ar / 25% CO ₂
GTAW	.093"	Direct Current; Electrode -			100% Ar
	.125"				

STANDARD PACKAGING

GMAW (MIG)	33-lb plastic spools	1,980-lb pallet
GTAW (TIG)	10-lb plastic tube	40-lb box

CLASSIFICATION

AWS/SFA 5.28, **Class ER90S-B91** (formerly ER90S-B9)

